



P25 – Joint Compound

A very fast gypsum base powder joint compound for bedding and finishing coat.

Technical Department of Siniat assures, through specific technical advices, the right application of the product in plasterboard systems about

acoustic and fire performances in according with detailed list of project and in conformity with body of legislation in use.

Technical Data

PRODUCT DESCRIPTION	Powder setting formulation to joint plasterboard with pregly tape
COMPOSITION	Gypsum based formulation
TIPOLOGY	Setting powder
CERTIFICATION	CE marking, product comply with standard European A3-EN 13963
COLOUR	White
PACKAGING CODE	P2505A bag of 5 Kg 28781 bag of 10 Kg
SHELF LIFE	9 months under right storage conditions (protect from hot and excessive heat)
RATIO J.C./PLASTERBOARD	0,38 [kg/sqm]
RATIO/EATER/POWDER 1° coat/sbsequent coat	0,55 [lit/Kg] / 0,60 [lit/Kg]
WORKABILITY TIME (*)	30 minutes
SETTING TIME (*)	60 minutes
MINIMUM WORK TEMPERATURE	> 5 [°C]
MAXIMUM WORK TEMPERATURE	< 40 [°C]
CLIMATE	Cold and temperete conditions
FIRE REACTION CLASS	A1
USE	Little and average jobsites
PREPARATION	-Manual Mix o r with mixer with low rpm (<800 rpm) - Cleans tools before use - Indoor local - With all plasterboard except SB board (look at technical data sheet application advice for other plasterboard) - For 1° coat and subsequent coat of plasterboard joint - With papaer tape - screws coverage
CARRY OUT	Manual

(*) Workability and setting time dipend on jobsite condition (temperature and umidity).

European Standard:
UNI EN 13963.

Joint Compaund tipology by ITT (Initial Type Test): 3B.

USE: Rapid setting powder joint compound, to prepare with water, used for joint manual treatment for 1° anf filling coat with reinforcement tape. For indoor. Particularly suitable for small to medium sized jobsites and average temperatures. Ideal for the tratments of the joint:between palsterboardspasterboard and existing support, for covered the screws. Micro perforated paper tape is raccomanded.

Contatti

ETEX BUILDING PERFORMANCE S.P.A.
Via Perlasca, 14
27010 Vellezzo Bellini (PV)
Tel. +39 0382 45 75 75
Fax +39 0382 45 75 250
siniat.italia@siniat.com

www.siniat.it

